

BASE COAT 309



SURFACE PREPARATION

Ensure the applied substrate is even and remove all dust, oil, grease and etc. Any free surface water must be removed before application.

MIXING RATIO

Add a 40kg of BASE COAT 309 to approximately 10 - 11 litres of clean water or 2.5 parts of Base COAT 309 to 1 part of water by volume. Use an electrical mixer to stir for 5 minutes to obtain a homogeneous paste of suitable consistency and it is ready for this plastering.

APPLICATION

Apply the properly mixed BASE COAT 309 material following normal plastering trade and craftsman practices. As BASE COAT 309 is a thin plaster, do not apply more than 2mm to 5mm per coat.

POT LIFE

Approximately one hour after mixing.

HANDLING

BASE COAT 309 is non-hazardous. In case of eye contact, wash with plenty of water. If Irritation persists, seek immediate medical attention.

DISCLAIMER

The use of this product is beyond the manufacturer's control and liability is restricted to the replacement of material proven faulty. The manufacturer is not responsible for any loss or damage arising from incorrect usage. Specifications are subjected to change without prior notice.